



ZAC Grenoble Air Parc Est
Avenue Louis Blériot
FR-38590 ST ETIENNE DE ST GEOIRS
Tél. : +33.(0)4.76.07.37.37
Fax : +33.(0)4.76.07.37.37
info@signs-europa.fr
www.signs-europa.fr

FICHE TECHNIQUE

BACHE LAMINEE FRONTLIGHT ECO - NF550

Laizes disponibles	1.10 m, 1.37 m, 1.60 m, 2.50 m & 3.20 m	Classe	Extérieur
Longueur	50 m	Mandrin	3 pouces (7.6 cm)

Description :	Bâche PVC extérieur pour impression numérique solvant et écosolvant.
----------------------	--

Caractéristiques	Data	Method
Support	PVC et Polyester Laminé	
Titre	500 D x 500 D	
Poids total	440 g/m ² (± 20)	FZ/T01003
Couleur	Blanc Mat	
Blancheur	82 ±5	
Résistance à la tension	Longueur : 850 N / 5 cm Largeur : 700 N / 5 cm	GB/T1040
Résistance à la déchirure	Longueur : 20 N / 5 cm Largeur : 50 N / 5 cm	GB/T16578
Allongement	15%	GB/T1040
Température	-20°C / +70°C	

NOTE :

Données non contractuelles, sous réserve de modification sans préavis. Il appartient à l'utilisateur de s'assurer de la compatibilité du produit avec son utilisation. Il est de la responsabilité du producteur de remplacer tout produit qui s'avérerait défectueux suite à un vice de fabrication.



ZAC Grenoble Air Parc Est
Avenue Louis Blériot
FR-38590 ST ETIENE DE ST GEOIRS
Tél. : +33.(0)4.76.07.37.37
Fax : +33.(0)4.76.07.37.37
info@signs-europa.fr
www.signs-europa.fr

DATA SHEET

FRONTLIGHT ECO LAMINATED - NF550

Available Widths	1.10 m, 1.37 m, 1.60 m, 2.50 m & 3.20 m	Classe	Outdoor
Lenght	50 m	Core	3 inches (7,6 cm)

Description :	Outdoor frontlight laminated PVC banner, for solvent and eco-solvent digital printing
----------------------	---

Item	Data	Method
Base	PVC and Laminated polyester	
Yarn	500 D x 500 D	
Total Weight	440 g/m ² (± 20)	FZ/T01003
Colour	Matt White	
Whiteness	82 ±5	
Tensile Strength	MD : 850 N / 5 cm CD : 700 N / 5 cm	GB/T1040
Tearing Strength	MD : 20 N / 5 cm CD : 50 N / 5 cm	GB/T16578
Elongation at break	15%	GB/T1040
Temperature	-20°C / +70°C	

NOTE :

The data are provided for information only, all details are subject to change without notice. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. The user of the product assumes the obligation to determine the suitability of the product for each particular application and assumes all risks and liability related to such use. It is producer's responsibility to the replacement of any product proven to be defective at the time of application due to a manufacturing anomaly.